

Waterborne

Product name
BURNOCK WD-569

Description

BURNOCK WD-569 is a waterborne OH functional acrylic dispersion to use in combination with polyisocyanates for 2K polyurethane coatings. BURNOCK WD-569 has excellent adhesion to plastics and water resistance. It is recommended for consumer electronics and home appliances.

Applications

Consumer electronics.
Home appliances.

Key features

Adhesion.
Water resistance.

Characteristics

	BURNOCK WD-569
Appearance	Milky white liquid
Solids content, weight %	39.0 - 41.0
Viscosity, mPa s 25°C	10 - 1000
pH	7.5 - 8.5
OH value on solids, mgKOH/g	32 (estimated value)
Solvent	Dipropylene glycol dimethyl ether (DMM) / Butyl acetate / Water

Storage

Store in a cool, dry, and well-ventilated place at temperatures below 40°C.

Safe handling note

Refer to SDS for BURNOCK WD-569.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

211108

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.