

**Solventborne** **High solids**

## Product name

# Idepoxyether-8432

### Description

Idepoxyether-8432 is a solventborne epoxy ether resin to use in combination with/without blocked isocyanates for 1K coatings and to use in combination with aromatic polyisocyanates or amino resins for 2K coatings. Idepoxyether-8432 has excellent anti-corrosion property. It is recommended for metal coatings.

### Applications

Primer for metal coatings.

### Key features

Anti-corrosion.

### Characteristics

	Idepoxyether-8432
Appearance	Clear liquid
Solids content, weight %	68.0 - 72.0
Viscosity, ford cup#4 seconds 30°C (40% resin solution in xylene)	25 - 35
Color, Gardner	12 max.
OH value on solids, mgKOH/g	45.0 - 50.0
Xylene tolerance	Infinite
Solvent	Xylene

### Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

### Safe handling note

Refer to SDS for Idepoxyether-8432.

Please confirm with our sales representative regarding chemical regulatory status of intended countries.

240219

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.

**DIC Corporation**For more information: <https://www.dic-global.com/en/products/coating.html>