TECHNICAL DATA SHEET





Light shielding and reflection adhesive tape

DAITAC[®] #8612EDX-W-100-2

Construction



PET release liner

Acrylic adhesive

PET film (black & white)

Acrylic adhesive

PET release liner

※Outside of a roll

Characteristics

- ✓ Good repulsion resistance.
- ✓ Prevent waving of prism sheet.
- ✓ Excellent light shielding
- ✓ Product does not use the 6 restrictive substances of the RoHS Directive.

Applications

- ✓ For bonding LCD module
- ✓ Great for bonding to areas that requires light shielding.

Properties

Test item	Condition	Substrate	Unit	#8612EDX-W-100-2
Thickness	Except release liner	-	μm	100
180 deg. peel strength	Conform to JIS Z0237	PC	N/20mm	17
		SUS (hairline)	N/20mm	14.5
Transmittance	Conform to JIS Z7361	-	%	< 0.1



980mm in max width

50m in length

DIC Corp.

Composite Materials Product Div. https://www.dic-global.com/en/products/adhesive_tapes,

Please note that the data provided in this catalog (the "Catalog") is offered for informational purposes only, and serves as an example of previously measured values and not guaranteed values. DIC Corporation ("DIC") does not and shall not guarantee suitability and compatibility of the Products and the materials that the buyer will incorporate the Products with. Please note that prior to any use of the products stated in the Catalog (the "Products"), it is the buyer's responsibility to confirm the suitability and compatibility of the Products and the materials that the buyer will incorporate the Products with. DIC may modify the specifications of the Products stated in the Catalog at any time and at DIC's sole discretion prior to any use of the products. DIC shall not be liable for any infringement on any third parties' intellectual property rights resulting from the Products' existence, sale, use, combination with any materials, or any other applications or the Products thereof. DIC is the owner of the copyright associated with this Catalog. Copying and/or reprinting this Catalog without obtaining prior permission in writing from DIC is strictly prohibited.