

**Solventborne**

**Product name**  
**ACRYDIC LA-9501-60C**

**Description**

ACRYDIC LA-9501-60C is a solventborne OH functional acrylic resin that can be used as a 1K lacquer or in combination with polyisocyanate for 2K polyurethane coatings. ACRYDIC LA-9501-60C has excellent adhesion to metals, high gloss and chemical resistance. It is recommended for direct to metal (DTM) applications.

**Applications**

Direct to metal (DTM).  
Interior and exterior decorative coatings.

**Key features**

High gloss.  
Adhesion to metals like zinc galvanized steel and aluminium.  
Chemical resistance.  
Flexibility.  
Can be used as 1K or 2K paint.

**Characteristics**

	<b>ACRYDIC LA-9501-60C</b>
Appearance	Clear liquid
Solids content, weight %	59.0 - 61.0
Viscosity, Gardner 25°C	Z3 - Z5
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	3.0 - 6.0
OH value on solids, mgKOH/g	Approx. 90
OH content on solids, %	Approx. 2.7
Specific gravity, 25°C	0.97 - 0.99
Solvent	Xylene / n-Butanol

**Storage**

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

**Safe handling note**

Refer to SDS for ACRYDIC LA-9501-60C.  
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210604

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.