Solventborne

Product name

ACRYDIC 55-129-HP

Description

ACRYDIC 55-129-HP is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC 55-129-HP has excellent weather resistance, leveling, and workability. It is recommended for automotive refinishing.

Applications

Automotive refinishing.
General industrial coatings.

Key features

Leveling.
Workability.
Weather resistance.

Characteristics

	ACRYDIC 55-129-HP
Appearance	Clear liquid
Solids content, weight %	64.0 - 66.0
Viscosity, Gardner 25°C	U - X
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	2.0 - 4.0
OH value on solution, mgKOH/g	47.0 - 54.0
Solvent	Butyl acetate / Toluene

Storage

Store in a cool, dry, well-ventilated place at temperatures below 30°C.

Safe handling note

Refer to SDS for ACRYDIC 55-129-HP.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.