

Solventborne **High solids**

Product name
ACRYDIC ZHP-2263

Description

ACRYDIC ZHP-2263 is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC ZHP-2263 has excellent appearance and fast drying properties. It is recommended for automotive refinishing clear topcoats.

Applications

Automotive refinishing clear topcoats.

Key features

Low VOC.
Appearance.
Fast drying.
BTX free.

Characteristics

	ACRYDIC ZHP-2263
Appearance	Clear liquid
Solids content, weight %	78.5 - 81.5
Viscosity, Gardner 25°C	Z2 - Z5
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	5.0 - 9.0
OH value on solution, mgKOH/g	121.0 - 131.0
Solvent	Butyl acetate

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC ZHP-2263.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.