

Non-solvent

Product name
BURNOCK D-161

Description

BURNOCK D-161 is a solvent free OH functional alkyd resin to use in combination with polyisocyanates for 2K polyurethane coatings. BURNOCK D-161 has excellent flexibility and chemical resistance. It is recommended for wood topcoats.

Applications

Wood topcoats.
Automotive interior.

Key features

Flexibility.
Chemical resistance.
Solvent free.

Characteristics

	BURNOCK D-161
Appearance	Clear liquid
Solids content, weight %	100
Viscosity, Gardner 25°C	Z5 - Z8
Color, Gardner	2 max.
Acid value on solution, mgKOH/g	4.5 max.
OH value on solution, mgKOH/g	155.0 - 180.0

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for BURNOCK D-161.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

220322

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.