



Color & Comfort

TECHNICAL DATA SHEET

Solventborne**High solids**

Product name

BURNOCK PE 6202

Description

BURNOCK PE 6202 is a solventborne branched polyester polyol. BURNOCK PE 6202 has excellent gloss and color retention. It is recommended as a modifier for polyester-melamine coil coating applications.

Applications

Coil Coatings.
Modifying resin.

Key features

In formulation, it exhibits high gloss and color retention.
Comparable properties to coconut melamine finishes.
Compatibility with various resins.
High-solids.

Characteristics

| | BURNOCK PE 6202 |
|--|------------------------|
| Appearance | Clear liquid |
| Solids content, weight % | 66.0 - 68.0 |
| Viscosity, Gardner (mPa s) 25°C | Z3 max. (4400) |
| Color, Gardner | 4 max. |
| Acid value on solids, mgKOH/g | 85.0 - 100.0 |
| OH value on solids, mgKOH/g | 8.0 - 15.0 |
| Density, g/cm³ | 1.046 |
| Solvent | Amyl acetate / Xylene |

Storage

Store in a cool, dry, well-ventilated place at temperatures below 30°C.

Safe handling note

Refer to SDS for BURNOCK PE 6202.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.

DIC CorporationFor more information: <https://www.dic-global.com/en/products/coating.html>

1 / 1