Solventborne UV Curable

Product name

LUXYDIR 17-806

Description

LUXYDIR 17-806 is a solventborne urethane acrylate UV curable resin. LUXYDIR 17-806 has excellent hardness, adhesion to plastics and chemical resistance. It is recommended for plastic substrates like PMMA, PC, ABS or unsaturated polyester.

Applications

Film coatings.
Automotive interior plastic parts coatings.
Home appliances.
Consumer electronics.

Key features

Hardness.
Fast curing.
Abrasion resistance.

Characteristics

	LUXYDIR 17-806
Appearance	Clear liquid
Solids content, weight %	78.0 - 82.0
Viscosity, Gardner 25°C	H - L
Color, Gardner	2 max.
Solvent	Butyl acetate

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for LUXYDIR 17-806.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.

DIC Corporation

For more information: https://www.dic-global.com/en/products/coating.html