

Solventborne

Product name
ALUKIDIR 16-141

Description

ALUKIDIR 16-141 is a solventborne medium oil alkyd resin to use with metal carboxylate driers for air drying coatings. ALUKIDIR 16-141 has excellent storage stability. It is recommended for architectural coatings.

Applications

Architectural coatings.

Key features

Storage stability.

Characteristics

	ALUKIDIR 16-141
Appearance	Light yellow clear liquid
Solids content, weight %	49.0 - 51.0
Viscosity, Gardner 25°C	Z1 - Z3
Color, Gardner	7 max.
Acid value on solution, mgKOH/g	6 max.
Type of oil	Linseed, Tall oil
Oil length, %	50
Solvent	White spirit / Xylene

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ALUKIDIR 16-141.

Please confirm with our sales representative regarding chemical regulatory status of intended countries.

220322

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.