

Solventborne

Product name
BURNOCK UL-65

Description

BURNOCK UL-65 is a solventborne oil modified polyurethane resin to use as air-drying enamel in combination with metal carboxylate driers. BURNOCK UL-65 has high gloss and excellent adhesion, hardness, abrasion resistance and chemical resistance. It is recommended for wooden floor coatings.

Applications

Wooden floor coatings.
Interior wood finishes.

Key features

Fast drying.
Chemical resistance.
Adhesion.
High gloss.
Recoatibility.
Abrasion resistance.

Characteristics

	BURNOCK UL-65
Appearance	Clear liquid
Solids content, weight %	59.0 - 61.0
Viscosity, Gardner 25°C	Z1 - Z3
Color, Gardner	5 max.
Acid value on solution, mgKOH/g	1.0 max.
Type of oil	Linseed
Oil length, %	65
Specific gravity, 25°C	0.91 - 0.93
Solvent	White spirit

Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

Safe handling note

Refer to SDS for BURNOCK UL-65.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.