

# TECHNICAL DATA SHEET



DIC PSAs  
web page




4A19A5 E Color & Comfort

Aluminum foil adhesive tape for EMI shielding

## DAITAC® 52050LA

### ■ Construction



### ■ Characteristics

- ✓ Excellent EMI shielding
- ✓ Good thermal conductivity
- ✓ Excellent adhesion

### ■ Applications

- ✓ For EMI shielding of electronic equipment.
- ✓ For heat spread application.

### ■ Properties

Test item	Condition	Substrate	Unit	52050LA
Thickness	Except release liner	-	μm	95
180 deg. peel strength	23°C, 1hr	SUS (hairline)	N/25mm	17.6
		AL	N/25mm	16
		ABS	N/25mm	16.1
		PS	N/25mm	16.2
		PC	N/25mm	17.4
		PP	N/25mm	15.4
Static shear	70°C, 0.5kg	SUS (hairline)	hr	24 <

■ **Remarks** UL510FR certified [File No.E-167390]

■ **Size** 1,000mm in max width 50m in length

**DIC Corp.**

Composite Solutions BU

[https://www.dic-global.com/en/products/adhesive\\_tapes/](https://www.dic-global.com/en/products/adhesive_tapes/)

Please note that the data provided in this catalog (the "Catalog") is offered for informational purposes only, and serves as an example of previously measured values and not guaranteed values. DIC Corporation ("DIC") does not and shall not guarantee suitability and compatibility of the Products and the materials that the buyer will incorporate the Products with. Please note that prior to any use of the products stated in the Catalog (the "Products"), it is the buyer's responsibility to confirm the suitability and compatibility of the Products and the materials that the buyer will incorporate the Products with. DIC may modify the specifications of the Products stated in the Catalog at any time and at DIC's sole discretion prior to any use of the products. DIC shall not be liable for any infringement on any third parties' intellectual property rights resulting from the Products' existence, sale, use, combination with any materials, or any other applications or the Products thereof. DIC is the owner of the copyright associated with this Catalog. Copying and/or reprinting this Catalog without obtaining prior permission in writing from DIC is strictly prohibited.