

Solvent-Resistant PANDEX 330: Properties and Formulation Options

Features

- Exhibits excellent chemical and solvent resistance.
- Enables the formulation of low-hardness polyurethane with minimal compression set.

PANDEX		330	
Viscosity @75°C	mPa·s	5000-10000	
Curing agent		MOCA	TMP
Hardness ¹⁾		85±2	51±2
Tensile strength	MPa	22	4
Tear Strength	kN/m	64	22
Rebound Resilience ²⁾	%	18	6
25% Compression set 22hr@70°C	%	22	3

1. JIS K 7312 A hardness, 2. ASTM D2632