

High-Durability PANDEX RV-5295: Properties and Hardness Range

MOCA-Free

Features

- Produces amine-free, TDI-free polyurethane with excellent durability.
- Offers flexible hardness variations through selection of different curing agents.

PANDEX		RV-5295		
Viscosity @80°C	mPa·s	1500-2500		
Curing agent		Curing agent A	Curing agent B	1,4BG
Hardness ¹⁾		85±2	90±2	95±2
Tensile strength	MPa	26	31	29
Rebound Resilience ²⁾	%	22	23	25

1. JIS K 7312 A hardness, 2. ASTM D2632

