

AMORVON WL-30 BLACK

- **Product Summary:** WL-30 BLACK is a glass fiber and polytetrafluoroethylene filled modified PPS compound with low friction and wear properties.
- **Color:** Black

Engineering Properties			
Properties	Test Method	Unit	Typical value
General Information			GF30%/PTFE, Modified PPS Precision molding Self-lubricant
Physical			
Density	ISO 1183-1	g/cm ³	1.69
Water absorption, 23°C /24hrs.	ISO 62	%	0.09
Mold shrinkage ^a	ISO 294-4	%	0.4/0.6
Mechanical			
Tensile strength	ISO 527-1,2	MPa	140
Tensile modulus	ISO 527-1,2	GPa	13.0
Tensile strain at break	ISO 527-1,2	%	1.4
Flexural strength	ISO 178	MPa	215
Flexural modulus	ISO 178	GPa	12.0
Flexural strain at flexural strength	ISO 178	%	1.7
Charpy impact strength, notched	ISO 179/1eA	kJ/m ²	8
unnotched	ISO 179/1eU	kJ/m ²	20
Co-eff. of friction ^b , static/dynamic	-	-	0.23/0.22
Thermal			
Temperature of deflection under load, 1.80MPa	ISO 75-1,2	°C	250
Co-eff. of linear thermal expansion ^a , -50~50 °C	ISO 11359-2	x 10 ⁻⁵ /K	1.5/4.5
Co-eff. of linear thermal expansion ^a , 100~200 °C	ISO 11359-2	x 10 ⁻⁵ /K	1.5/9.0
Flammability ^c /thickness (mm)	UL-94	-	V-0 equivalent/0.75
Electrical			
Electric strength, t=1.0mm	IEC 60243-1	kV/mm	23
Relative permittivity, 1MHz	IEC 62631-2-1	-	4
Dielectric dissipation factor, 1MHz	IEC 62631-2-1	-	0.006
Comparative Tracking Index (CTI)	IEC 60112	V	150
Volume resistivity	IEC 62631-3-1	Ω·cm	10 ¹⁶
Molding Condition			
Cylinder temperature	-	°C	290-320
Mold temperature	-	°C	130-150

a: Flow direction/Transverse direction

b: P=150kPa, V=0.3m/s, PPS vs. carbon steel

c: Own data