

FZ-3805-A1 BLACK-U

- **Product Summary:** FZ-3805-A1-U is a glass fiber and mineral filled low halogen type of PPS compound with dimensional stability and low warpage.
- **Color:** Black

Engineering Properties

Properties	Test Method	Unit	Typical value
General Information			GF/Filler Cl; <900ppm Low warpage Low flash
Physical			
Density	ISO 1183-1	g/cm ³	1.94
Water absorption, 23°C /24hrs.	ISO 62	%	0.03
Mold shrinkage ^a	ISO 294-4	%	0.3/0.6
Mechanical			
Tensile strength	ISO 527-1,2	MPa	115
Tensile modulus	ISO 527-1,2	GPa	19.0
Tensile strain at break	ISO 527-1,2	%	0.9
Flexural strength	ISO 178	MPa	220
Flexural modulus	ISO 178	GPa	18.5
Flexural strain at flexural strength	ISO 178	%	1.3
Charpy impact strength, notched	ISO 179/1eA	kJ/m ²	6
unnotched	ISO 179/1eU	kJ/m ²	20
Co-eff. of friction ^b , static/dynamic	-	-	0.35/0.35
Thermal			
Temperature of deflection under load, 1.80MPa	ISO 75-1,2	°C	275
Co-eff. of linear thermal expansion ^a , -50~50 °C	ISO 11359-2	x 10 ⁻⁵ /K	1.5/2.5
Co-eff. of linear thermal expansion ^a , 100~200 °C	ISO 11359-2	x 10 ⁻⁵ /K	1.5/7.0
Flammability ^c /thickness (mm)	UL-94	-	V-0/0.40
Electrical			
Electric strength, t=1.0mm	IEC 60243-1	kV/mm	21
Relative permittivity, 1MHz	IEC 62631-2-1	-	5
Dielectric dissipation factor, 1MHz	IEC 62631-2-1	-	0.003
Comparative Tracking Index (CTI)	IEC 60112	V	225
Volume resistivity	IEC 62631-3-1	Ω·cm	10 ¹⁶
Molding Condition			
Cylinder temperature	-	°C	290-320
Mold temperature	-	°C	130-150

a: Flow direction / Transverse direction

b: P=150kPa, V=0.3m/s, PPS vs. carbon steel

c: UL file No. E53829