


TECHNICAL INFORMATION

4F50A5E

Electrically conductive copper foil adhesive tape



Construction



Characteristic


- Tape thickness is 65μm.
- Excellent electrical conductivity in thickness direction.
- Excellent adhesive strength .

Application

For EMI shielding of electronic equipment.

Property

	Units	E65CU
Tape thickness	μm	65
Adhesion (SUS)	N/25mm	12.8
Electrical Conductivity: Pressure Method	$\Omega/6.25$ c m 2	0.01
Electrical Conductivity: Attached Method	$\Omega/6.25$ c m 2	0.03
Holding power: 70°C 0.5kg	h	24<



1000mm in max width / 50m in length

DIC Corporation Composite Material Product div. http://www.dic-global.com/en/

Items mentioned in this information are for customers' reference and limited to certain examples although they are based on the most reliable data obtained by our company. It is hoped that customers make the best use of these products after careful examination. Concerning to use and processing the products on this documents, it is not guaranteed a industrial ownerships of a third party. All recipes and processes should be modified, if necessary to conform with particular application.